

Deltron® Velocity Premium Clearcoat LV

DC4010

DC4010 is a high velocity, premium clearcoat, specifically developed to enhance productivity in air-dry and low bake collision repair facilities.

Deltron® DC4010 high velocity premium clearcoat offers ease of application, outstanding flow and leveling, superior clarity and a deep rich gloss. DC4010 is extremely versatile and can be used for multi-panel and overall refinishing.

While offering good air-dry performance, DC4010 is best suited for low bake or force dry conditions. DC4010 has an extremely short bake cycle, which reduces in-booth time, energy cost and can improve paint shop productivity.

DC4010 is designed to meet the most stringent VOC laws in Southern California.



Features

- Low temperature, fast bake
- Easy application

Advantages

- Process time savings
- Less rework

Benefits

- Customer satisfaction

Compatible Surfaces

DC4010 may be applied over:

- *DELTRON®* (DBU) Universal Basecoat
- *DELTRON®* 2000 (DBC) Basecoat

Required Products

	Hardener
Low Temperature	DCH3510 (55° – 75°F / 13° – 24°C)
Medium Temperature	DCH3520 (75° – 95°F / 24° – 35°C)
High Temperature	DCH3530 (95° F / 35°C & above)

DC4010

Directions for Use

Preparation:

Where VOC limits allow a maximum of 3.5 lbs./US Gal. for multi-stage systems, reduce DBU Color 100% with DRR Reducer or DBC Color 100% with DT Reducer. Refer to the Product Information Bulletin of the color system for its application, dry times, and blend recommendations. (See P-175CA for DBC and P-152 for DBU Color).

Mixing Ratio:



Standard Mix

DC4010 : DCH3510/DCH3520/DCH3530
4 : 1



Pot life is 2½ – 3 hours at 70°F (21°C) for standard mix

Additives:



With DX814 Flexibilizer

DC4010 : DCH Hardener : DX814
3 : 1 : ½

Application:



Apply: 2 wet coats

Air Pressure:

HVLP: 10 PSI at the air cap
Conventional: 45 – 55 PSI at the gun







Spraygun Set-up:



Fluid Tip: 1.3 – 1.5 mm or equivalent
Film build per wet coat: 3.0 – 3.5 mils
Dried film build per coat: 1.2 – 1.4 mils

Directions for Use

Drying times:

	Between coats:	5 – 7 minutes
	Dust-free: 70°F / 21°C	15 – 25 minutes
	Tack Free: 70°F / 21°C	30 – 45 minutes
	Tape Time: 70°F / 21°C	12 – 16 hours
	Air Dry: 70°F / 21°C	4 – 6 hours
	Force Dry: Purge Bake w/3510 Bake w/3520 or 3530	None 10 minutes @140°F (60°C) 20 minutes @140°F (60°C)
	IR (Infrared): Medium wave Short wave	5 minutes half bake, 10 minutes full 5 minutes
	Polishing: Air Dry Force Dry	4 – 6 hours @ 70° F (21°C) Immediately after cool down DC4010 can be lightly sanded with 1500 – 2000 grit sandpaper and compounded. Use a foam pad with a minor cutting compound to remove any minor imperfections.
	Repair and Recoat:	Recoat after force dry and cooling cycle or 4 – 6 hours air dry 70°F (21°C). Repair after force dry and cooling cycle or 4 – 6 hours air dry 70°F (21°C). DC4010 must be sanded before recoating with primer, color or clear.

Note: All force dry times are quoted for metal temperature. Additional time must be allowed during force dry to allow metal to reach recommended temperature.

Equipment Cleaning:

Spray guns, gun cups, storage pots, etc. should be cleaned thoroughly after each use with any appropriate PPG General Purpose Solvent.

Technical Data:

VOC less exempt solvents (Package)	2.70 lbs / U.S.Gal (324 grams/liter)
VOC less exempt solvents (Applied 4:1)	2.05 lbs / U.S.Gal (246 grams/liter)
VOC less exempt solvents w/DX814 (Applied 3:1:1/2)	2.50 lbs / U.S.Gal (300 grams/liter)
Total Solids by Volume (Applied 4:1)	38.01%
Sq. Ft Coverage / US Gal (Applied 4:1) (1 mil, 100% transfer efficiency)	609

DC4010

Deltron®
Velocity Premium Clearcoat LV

Resistance Testing:

Treated steel panels used for evaluation were primed with Original Equipment *UNIPRIME®*, *DELTRON®* Sealer and topcoated with *DELTRON®* Basecoat prior to DC4010 Clearcoat. All resistance results were obtained after DC4010 Clearcoat had been allowed to dry approximately 72 hours at moderate temperatures (70°F/21°C).

Important:

The contents of this package must be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

See Material Safety Data Sheet and Labels for additional safety information and handling instructions.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

PPG Automotive Refinish

World Leaders In Automotive Finishes

PPG Industries
19699 Progress Drive
Strongsville, OH 44149

PPG Canada Inc.
2301 Royal Windsor Drive
Mississauga, Ontario L5J 1K5