



# OneChoice™

A Universal Ancillary Brand

## OC-2

### Universal Matting Agent

#### SU4985 Universal Matting Agent

SU4985 Universal Matting Agent is designed for use across product lines with compatible PPG clears and color systems. Mixing in the SU4985 will produce varying degrees of flatness.



#### Features

- Easy mixing ratios
- Produces consistent results

#### Advantages

- Can be used in *Deltron*®, *Global* or *Omni*™ systems
- Gets the job done right

#### Benefits

- Customer satisfaction
- Versatility and reliability

#### Required Products

- SU4985 Universal Matting Agent

#### Related Products

- Recommended PPG brand clears and topcoats

#### Compatible Products

The *One Choice*® *Universal Matting Agent* is for universal use with PPG brand clears and topcoats.

*Note: When adding SU4985 to recommended PPG clears and topcoats, please refer to the products specific technical bulletin for proper application.*



**Application Data**

The following chart indicates the number of ounces of SU4985, reducer and hardener to be added to **1 quart (32 oz) of clear** to achieve varying degrees of flatness. Unless otherwise specified, the types of reducer and hardener used for a particular system will appear on the product bulletin for that system. Changing the amount of color or clear will increase or decrease the number of ounces of SU4985, reducer and hardener.

**Based on 60° Gloss Meter**

Flat = 0 - 5° Gloss

Eggshell = 20 - 30° Gloss

Semi-gloss = 50 - 60° Gloss

Deltron Product Mixes	Gloss	Ounces of SU4985	Ounces of Reducer	Ounces of Hardener	Mix Ratio by Parts	VOC Less Water, Less Exempt lbs/gal (g/l)	Bulletin #
<b>DCU2021</b>	Flat	59	8	8	4 : 7 : 1 : 1	4.92 (590)	P-199
	Eggshell	48	8	8	4 : 6 : 1 : 1	4.84 (580)	
	Semi-gloss	39	8	8	4 : 5 : 1 : 1	4.77 (572)	
<b>DCU2042</b>	Flat	52	8	8	4 : 6 : 1 : 1	4.87 (584)	P-216
	Eggshell	44	8	8	4 : 5 : 1 : 1	4.81 (576)	
	Semi-gloss	30	8	8	4 : 4 : 1 : 1	4.67 (560)	
<b>DC3000</b>	Flat	39	0	8	4 : 5 : 0 : 1	4.81 (576)	P-236
	Eggshell	35	0	8	4 : 4 : 0 : 1	4.76 (570)	
	Semi-gloss	28	0	8	4 : 3 : 0 : 1	4.67 (560)	
<b>DC4000</b>	Flat	39	0	8	4 : 5 : 0 : 1	4.89 (586)	P-241
	Eggshell	35	0	8	4 : 4 : 0 : 1	4.85 (581)	
	Semi-gloss	28	0	8	4 : 3 : 0 : 1	4.77 (572)	
<b>DC3010</b>	Flat	39	0	8	4 : 5 : 0 : 1	4.33 (519)	P-242
	Eggshell	32	0	8	4 : 4 : 0 : 1	4.16 (499)	
	Semi-gloss	21	0	8	4 : 3 : 0 : 1	3.80 (455)	
<b>DC4010</b>	Flat	39	0	8	4 : 5 : 0 : 1	4.33 (519)	P-243
	Eggshell	32	0	8	4 : 4 : 0 : 1	4.17 (500)	
	Semi-gloss	21	0	8	4 : 3 : 0 : 1	3.80 (455)	
<b>DCU2002</b>	Flat	75	8	8	4 : 9 : 1 : 1	5.01 (600)	P-200
	Eggshell	59	8	8	4 : 7 : 1 : 1	4.92 (590)	
	Semi-gloss	48	8	8	4 : 6 : 1 : 1	4.84 (580)	
<b>DCU2010</b>	Flat	48	0	8	4 : 7 : 0 : 1	4.42 (530)	P-228CA
	Eggshell	39	0	8	4 : 6 : 0 : 1	4.26 (511)	
	Semi-gloss	32	0	8	4 : 5 : 0 : 1	4.09 (490)	
<b>DCC Color</b>	Flat	37	5	10	3 : 3½ : ½ : 1	4.78 (573)	P-168
	Eggshell	32	5	10	3 : 3 : ½ : 1	4.73 (567)	
	Semi-gloss	16	5	10	3 : 1½ : ½ : 1	4.52 (542)	

## Application Data

Global Product Mixes	Gloss	Ounces of SU4985	Ounces of Reducer	Ounces of Hardener	Mix Ratio by Parts	VOC Less Water, Less Exempt lbs/gal (g/l)	Bulletin #
<b>D8150</b>	Flat	66	8	8	4 : 8 : 1 : 1	4.83 (579)	EU139
	Eggshell	50	8	8	4 : 6 : 1 : 1	4.69 (562)	
	Semi-gloss	33	8	8	4 : 4 : 1 : 1	4.50 (539)	
<b>D893</b>	Flat	66	8	8	4 : 8 : 1 : 1	5.00 (599)	EU112
	Eggshell	50	8	8	4 : 6 : 1 : 1	4.91 (588)	
	Semi-gloss	33	8	8	4 : 4 : 1 : 1	4.76 (570)	
<b>D894</b>	Flat	66	8	8	4 : 8 : 1 : 1	4.96 (594)	EU100
	Eggshell	50	8	8	4 : 6 : 1 : 1	4.86 (582)	
	Semi-gloss	33	8	8	4 : 4 : 1 : 1	4.71 (564)	
<b>D8121</b>	Flat	41	8	8	4 : 5 : 1 : 1	4.61 (552)	EU141
	Eggshell	33	8	8	4 : 4 : 1 : 1	4.49 (538)	
	Semi-gloss	25	8	8	4 : 3 : 1 : 1	4.34 (520)	
<b>DG Color</b>	Flat	37	5	10	3 : 3½ : ½ : 1	4.57 (548)	EU01
	Eggshell	32	5	10	3 : 3 : ½ : 1	4.56 (546)	
	Semi-gloss	16	5	10	3 : 1½ : ½ : 1	4.52 (542)	

Omni Product Mixes	Gloss	Ounces of SU4985	Ounces of Reducer	Ounces of Hardener	Mix Ratio by Parts	VOC Less Water, Less Exempt lbs/gal (g/l)	Bulletin #
<b>MAE</b>	Flat	24	8	8	4 : 3 : 1 : 1	5.07 (608)	OB16
	Eggshell	16	8	8	4 : 2 : 1 : 1	5.01 (600)	
	Semi-gloss	8	8	8	4 : 1 : 1 : 1	4.93 (591)	
<b>MTK</b>	Flat	24	8	8	4 : 3 : 1 : 1	5.17 (620)	OB09
	Eggshell	16	8	8	4 : 2 : 1 : 1	5.11 (612)	
	Semi-gloss	8	8	8	4 : 1 : 1 : 1	5.05 (605)	
<b>MTV</b>	Flat	24	8	8	4 : 3 : 1 : 1	4.17 (500)	OB34
	Eggshell	16	8	8	4 : 2 : 1 : 1	3.98 (477)	
	Semi-gloss	8	8	8	4 : 1 : 1 : 1	3.72 (446)	
<b>MC260</b>	Flat	75	0	16	2 : 4½ : 0 : 1	5.09 (610)	OB32
	Eggshell	39	0	16	2 : 2½ : 0 : 1	4.88 (585)	
	Semi-gloss	26	0	16	2 : 1½ : 0 : 1	4.75 (569)	
<b>MC262</b>	Flat	40	0	8	4 : 9 : 0 : 1	4.76 (570)	OB37
	Eggshell	24	0	8	4 : 5 : 0 : 1	4.29 (514)	
	Semi-gloss	8	0	8	4 : 3 : 0 : 1	3.94 (472)	
<b>MC161</b>	Flat	75	0	16	2 : 4½ : 0 : 1	5.09 (610)	OB02
	Eggshell	39	0	16	2 : 2½ : 0 : 1	4.88 (585)	
	Semi-gloss	26	0	16	2 : 1½ : 0 : 1	4.76 (570)	
<b>JC620</b>	Flat	24	0	8	4 : 3 : 1 : 1	5.08 (609)	SL620
	Eggshell	16	0	8	4 : 2 : 1 : 1	5.02 (602)	
	Semi-gloss	8	0	8	4 : 1 : 1 : 1	4.92 (590)	
<b>JC630</b>	Flat	24	8	8	4 : 3 : 1 : 1	5.10 (611)	SL630
	Eggshell	16	8	8	4 : 2 : 1 : 1	5.04 (604)	
	Semi-gloss	8	8	8	4 : 1 : 1 : 1	4.95 (593)	
<b>JC780</b>	Flat	24	8	8	4 : 3 : 1 : 1	4.71 (564)	SL780
	Eggshell	16	8	8	4 : 2 : 1 : 1	4.54 (544)	
	Semi-gloss	8	8	8	4 : 1 : 1 : 1	4.28 (513)	
<b>JC781</b>	Flat	24	8	8	4 : 3 : 1 : 1	4.74 (569)	SL781
	Eggshell	16	8	8	4 : 2 : 1 : 1	4.57 (548)	
	Semi-gloss	8	8	8	4 : 1 : 1 : 1	4.31 (517)	

### Drying Times:

Follow the normal dry times for the PPG System's clear or topcoat.

**Technical Data:**

<b>Total dry film build:</b>	
Minimum	2.0 mils
Maximum	3.0 mils
Film build per wet coat	2.4 – 3.5 mils
Dried film build per coat	1.0 mil
<b>Theoretical coverage</b>	463 – 670 sq.ft./U.S. gallon
<i>(Theoretical coverage in sq.ft./U.S. gallon Ready-to-spray (RTS), giving 1 mil dry film thickness).</i>	
<b>Percent solids by volume RTS</b>	28.9 – 41.8%
<b>VOC</b>	
SU4985 (Pkg)	5.58 lbs. per U.S. gal. (669 g/l)

---

**See material Safety Data Sheet and Labels for additional safety information and handling instructions.**

---

**EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434 -4515. IN CANADA (514) 645-1320**

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

## PPG Industries

*World Leaders in Automotive Finishes*

PPG Industries  
19699 Progress Drive  
Strongsville, OH 44149  
1-800-647-6050

PPG Canada Inc.  
2301 Royal Windsor Drive  
Mississauga, Ontario, Canada L5J 1K5  
1-888-310-4762