

## JC630 4.2 Polyurethane Clearcoat

### Background

JC630 is a two component 4.2 VOC polyurethane clearcoat that is designed to maximize speed and appearance and may be used in either cross flow, air dry or downdraft force cure spray booths.

### JC630 4.2 Polyurethane Clearcoat

#### Clear

JC630 4.2 Polyurethane Clearcoat

#### Hardener

JH6360 4.2 Polyurethane Hardener-Fast

JH6370 4.2 Polyurethane Hardener-Medium

JH6380 4.2 Polyurethane Hardener-Slow

### Compatible Substrates

Automotive Refinish Basecoats

### Preparation

Allow basecoat color a minimum of 30 minutes and a maximum of 24 hours before clearing. After 24 hours the basecoat should be lightly sanded before applying JC630.

### Mixing

#### Ratios



JC630 : JH63XX  
4 : 1



Pot life is 1.5 - 2 hours at 70°F (21°C)

**Additives** JX993 10% to RTS quart  
JX994 0.5 oz. to RTS quart

### Clean Up

Clean spray guns, gun cups, storage pots thoroughly with JR Reducers, General Purpose Solvent or other appropriate clean up solvent after each use. Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

### Application

#### Coats



2 - 3 full wet coats

#### Air pressure



HVLP 8 - 10 psi at the air cap  
Conventional 50 - 60 psi at the gun

#### Gun setup

1.3 - 1.5 mm or equivalent

### Dry Times

#### Between coats



5 - 10 minutes at 70°F (21°C)

#### With JH6360 Hardener



Dust: 5 - 10 minutes  
Tack: 30 - 50 minutes  
Tape: 2 - 4 hours  
Polish: 2 - 4 hours  
Force dry: 15 min. at 140°F (60° C)  
Recoat: 8 hours or overnight at 70°F (21°C)

#### With JH6370 and JH6380 Hardeners



Dust: 10 - 15 minutes  
Tack: 50 - 60 minutes  
Tape: 2 - 4 hours  
Polish: 6 - 8 hours  
Force dry: 20 min at 140°F (60° C)  
Recoat: 8 hours or overnight at 70°F (21°C)

#### IR (Infrared)

12 - 15 minutes

### Properties

#### VOC

Package 3.54 lbs/gal (424 gm/l)  
Applied Less exempts 4:1 4.18 lbs/gal (501 gm/l)

#### Film build per coat

Applied 4:1 1.2 mils

#### Square foot coverage at 1 mil

Applied 4:1 560 sq. ft. / gal., no transfer loss

### Precautionary Information:

The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

### Medical Response:

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320.

### Material Safety Data Sheet:

Material Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG ShopLine™ Distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your ShopLine™ Distributor for the most up-to-date information.