



Specialty  
Performance Products

## Flexible Sealer

# SXA1043 Aerosol

## PD-703

SXA1043 Flexible Sealer was developed to provide a single component flexible sealer for use on repaired bumpers prior to using SX1044 High Build Flexible Surfacer.

### FEATURES:

- Single component, flexible
- Packaged in aerosol cans
- No additional flex add needed
- Eliminates sand scratch swelling

### COMPATIBLE SURFACES:

- Cured and sanded OEM finishes (except lacquer)
- Cured and sanded refinish topcoat systems

### RELATED PRODUCTS:

- SX1002 Sanding Paste
- SX1004 Plastic Cleaner and Prep
- SX1044 High Build Flexible Surfacer

### SURFACE PREPARATION:



1. Apply **SX1002 Sanding Paste** and abrade with a gray scotchbrite pad, then rinse thoroughly with water. Blow off surface.
2. Clean with **SX1004 Plastic Cleaner and Prep**.



3. Sand with 400 grit paper, blow off and re-clean with **SX1004**.

### APPLICATION PROCEDURE:



1. Apply 1-2 medium coats of **SXA1043 Flexible Sealer**.
2. Apply 1 – 2 coats of SX1044 as needed
3. Topcoat with choice of appropriate PPG Topcoat System.



Between coats: 5-10 minutes  
 Dust Free: 10 minutes  
 Air Dry: Allow 30 minutes drying time before priming  
 Fluid Tip: 1.3-1.5 mm or equivalent

#### Attention:

*When finished spraying aerosol products, hold can upside down and spray until valve is cleared. This will prevent clogging of the internal valve.*

### COMPATIBLE TOPCOATS:

- CONCEPT® (DCC) Acrylic Urethane
- CONCEPT® LV (CLV) Acrylic Urethane Color
- Delstar® / Delthane® (DAR/DXR80)
- Delstar® Acrylic Enamel
- Deltron® 2000 (DBC) Basecoat
- Deltron® (DBU) Universal Basecoat
- Omni™ (MBC) Acrylic Basecoat
- Omni™ (MTK) Acrylic Urethane
- Omni™ (MLV) Low VOC Urethane
- Omni™ (MAE) Acrylic Enamel
- Omni™ (MAE/MH) Acrylic Enamel
- Omni™ (MCV) Acrylic Urethane
- Omni™ (MCV) High Solids Urethane
- Omni™ (MCV) Basecoat
- Global (BC) Basecoat Color
- Global (DG) Direct Gloss Color
- Global (DGLV) Direct Gloss LV Color
- Delta® 2800(DHS) 2.8 VOC Polyurethane
- Delta® 3500(DUHS) High Solids Polyurethane
- Delta® (DUHS) High Solids Polyurethane Basecoat
- Delta® (DFHS) Fast Dry High Solids Polyurethane
- Delta® (DGHS) Chemical Resistant Polyurethane
- Delta® (DSS) Medium Solids Polyurethane
- Delta® (DVHS) Fast Dry 2.8 VOC Polyurethane



# Flexible Sealer

---

**PROPERTIES:**

---

<b>PRODUCT</b>	<b>Packaged VOC (lbs./US Gal.)</b>	<b>Volume Solids (RTS)</b>	<b>SQ. FT Coverage @ 1 mil (100% transfer efficiency)</b>
SXA1043	5.9	3.84	61

---

**See Material Safety Data Sheet and Labels for additional safety information and handling instructions.**  
EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (304) 843-1300. IN CANADA (514) 645-1320.  
PPG Industries, 19699 Progress Drive, Strongsville, Ohio, 44136  
PPG Canada Inc. 1330 Castlefield Avenue, Toronto, Ontario M6B 4B3

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.